

Polyester

Technische specificaties

Soortelijk gewicht	1.38
Smeltpunt	250 °C
Rekpercentage	30% - 35%
Kleur	Wit
Constructie	3-strengs geslagen of 8- en 12-strengs gevlochten "Leomax"

Diameter in mm	Omtrek inches	Gewicht % mtr.	Min. breekkracht Kgf.	Min. breekkracht kN.
8	1	5.1	1275	12.5
10	1 1/4	8.1	1990	19.5
12	1 1/2	11.6	2840	27.8
14	1 3/4	15.7	3975	39.0
16	2	20.5	5075	49.7
18	2 1/4	26.0	6350	62.2
20	2 1/2	32.0	7940	77.8
22	2 3/4	38.4	9525	93.3
24	3	46.0	11425	112.0
26	3 1/4	53.7	13340	130.7
28	3 1/2	63.0	15250	141.5
30	3 3/4	72	17145	168.0
32	4	82.0	19625	192.4
34	4 1/4	93.0	21875	214.4
36	4 1/2	104	24125	236.5
38	4 3/4	116	27000	264.7
40	5	128	29875	292.8
44	5 1/2	155	35500	348.0
48	6	185	48600	476.4
52	6 1/2	215	56700	555.8
56	7	251	65700	644.1
60	7 1/2	288	72300	708.8
64	8	328	80700	791.1
68	8 1/2	372	91000	892.1
72	9	415	99500	975.4
80	10	512	121900	1195.1
88	11	619	146300	1434.3
96	12	735	173400	1700.0
112	14	1000	234400	2298.0
120	15	1150	268000	2627.4
128	16	1310	303200	2972.5
144	18	1660	383200	3756.8
160	20	2050	474100	4648.0
176	22	2350	543500	5328.4