

Polypropyleen (gespleten film)

Technische specificaties

Soortelijk gewicht	0.91
Smeltpunt	160 °C
Rekpercentage	30%
Kleur	zalm en oranje
Constructie	3-strengs geslagen of 8- en 12-strengs gevlochten "Leomax"



Diameter mm.	Omtrek inches	Gewicht % mtr.	Min. breekkracht Kgf.	Min. breekkracht kN.
8	1	3.0	960	9.41
10	1 1/4	4.5	1425	14.0
12	1 1/2	6.5	2030	19.9
14	1 3/4	9.0	2790	27.4
16	2	11.5	3500	34.3
18	2 1/4	14.8	4450	43.6
20	2 1/2	18.0	5370	52.7
22	2 3/4	22.0	6500	63.7
24	3	26.	7600	74.5
26	3 1/4	31	8850	86.8
28	3 1/2	35.5	10100	99.0
30	3 3/4	41.0	11500	112.7
32	4	46.0	12800	125.4
36	4 1/2	58.5	16100	157.8
40	5	72.0	19400	190.2
44	5 1/2	88.0	23400	229.4
48	6	104	27200	266.6
52	6 1/2	122	31500	308.8
56	7	142	36000	352.9
60	7 1/2	163	41200	403.9
64	8	185	46600	451.8
68	8 1/2	210	52600	515.6
72	9	234	58500	573.5
80	10	290	72000	705.8
88	11	351	86400	847.0
96	12	417	102000	1000.0
104	13	482	118000	1151.8
112	14	568	138000	1352.9
120	15	648	156000	1529.4
128	16	740	176000	1725.4
136	17	838	197600	1937.2
144	18	940	219600	2152.9
152	19	1047	242000	2372.5
160	20	1160	266200	2609.8

